



GEON® HC Vinyl Materials

Vinyl-Based Formulations for Healthcare & Medical Applications

Engineered exclusively for the healthcare market, GEON HC Vinyl is the ideal material for a wide range of medical applications. It is proven as a safe and durable solution and is formulated to meet stringent healthcare safety requirements as defined by numerous agencies. These include the FDA, USP, UL, NSF, the European Commission, and the U.S. Consumer Product Safety Commission.

Formulations include flexible non-phthalate and non-ortho-phthalate vinyl options to meet various medical device applications or needs.

GEON HC FLEXIBLE VINYL MATERIALS

Flexible materials for a wide-range of medical applications including tubing, connectors and face masks.

- Broad durometer range (55A to 95A)
- Transparent or opaque colors, ETO sterilizable
- USP Class VI and gamma-stable grades

GEON HC NON-PHTHALATE AND NON-ORTHO-PHTHALATE VINYL MATERIALS

Specifically formulated for healthcare applications where a non-phthalate or non-ortho-phthalate plasticizer system may be desired.

- Broad durometer range (55A to 95A)
- Hemocompatible and gamma-stable grades
- Custom formulations available

GEON HC RIGID VINYL MATERIALS

Great balance of performance and cost for molded medical device housings.

- Inherent flame resistance and good chemical resistance
- Design flexibility and excellent aesthetics
- Printable, weldable, and bondable for safe and effective connections with other components

A SMART CHOICE

The inherent properties of vinyl polymer provide excellent performance, including exceptional resistance to flame, chemicals, and light. Vinyl has been a vitally important material for over 50 years and is tested and approved for use in many medical products today.

Vinyl can be safely processed, is recyclable, and provides a sustainable, environmentally acceptable solution.

The material grades highlighted below represent a sampling of the broad range of properties available within our vinyl materials portfolio; additional grades are available. In addition, we can work with you to create a custom solution for your performance needs.

DUROMETER (15 SEC)	MATERIAL #	GAMMA-STABLE	PLASTICIZER TYPE	EXAMPLE APPLICATIONS†
55A	HC65500	HC65500G	DOTP	Soft tubing, molding applications, oxygen masks
60A	HC66000	HC66000G	DOTP	Soft tubing, molding applications, oxygen masks
65A	HC66500	HC66500G	DOTP	Medium soft tubing, molding applications, oxygen masks
70A	HC67000	HC67000G	DOTP	Medium soft tubing, molding applications, oxygen masks
75A	HC67500	HC67500G	DOTP	Medium soft tubing, molding applications, oxygen masks
80A	HC68000	HC68000G	DOTP	Medium stiff tubing, molding applications, endotracheal tubing, drip chambers, connectors, catheters, bags
85A	HC68500	HC68500G	DOTP	Medium stiff tubing, molding applications, endotracheal tubing, drip chambers, connectors, catheters, bags
90A	HC69000	HC69000G	DOTP	Stiff tubing, molding applications, drip chamber components, catheters, luers, and connectors
95A	HC69500	HC69500G	DOTP	Stiff tubing, molding applications, drip chamber components, catheters, luers, and connectors

All listed products are made with FDA-sanctioned raw materials, and produced on medical manufacturing lines that employ Good Manufacturing Practices (GMP). In addition, we can work with you to create a custom solution for your performance needs.

† It is the customer's responsibility to ensure the material is suitable for the intended application.

1-888-910-0536
WWW.GEON.COM



Copyright © 2019, GEON Performance Solutions. GEON Performance Solutions makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. GEON makes no warranties or guarantees respecting suitability of either GEON's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. GEON MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.