



## Plenstar™ Series

### Plenum Fire Resistance Rated Cable

GEON® Plenstar vinyl formulations for plenum applications answer the need for flame and smoke performance requirements. They meet UL approvals for plenum and satisfy all physical properties for telecommunication cables. Addressable applications are Cat 3 to Cat 6 multi-conductor cables with a 75°C UL temperature rating, passing UL 444.

The Plenstar Series includes five grades of plenum jacketing cable compounds. Customization is also possible for modified performance enhancements to meet flame and smoke requirements. Custom colors can also be developed.

For manufacturers of telecommunication cables, Plenstar formulations offer the same reliability, quality, and convenience customers can expect with any product from the GEON family of products. Dedicated technical support and customer service is offered from design through processing for quicker issue resolution and faster time to production.

#### KEY CHARACTERISTICS

- Engineered to meet flame performance and physical properties for telecommunication cables
- Designed to meet UL approvals for plenum including UL13 as well as NFPA 262 requirements
- Multiple grades of plenum compounds for Cat 3 to Cat 6 applications

#### APPLICATIONS

The Plenstar Plenum Series is specifically formulated for plenum applications in telecommunications and copper wire.

## TECHNICAL PROPERTIES

Plenum jacket designed to meet NFPA 262 insulated twisted pairs for Cat 3/5/5E/6 CMP type constructions

Grade	Temp. Rating (°C)	S.G. (g/cc)	LTB (°C)	LOI (%)	Tensile (psi)	Elongation (%)	Duro Scale (A/D)	Duro 15 Sec.	Melt Temp. (°C)	Jacket/ Insulation/ Molding	Agency Listing
GEON WJJP603	75	1.63	-7	56	2200	250	D	55	170	J	UL
GEON WJJP620	75	1.62	-6	41	2500	180	D	54	170	J	
GEON WJJP621	75	1.63	-7	47	2300	150	D	54	170	J	
GEON WJJP622	75	1.59	-7	41	2600	200	D	56	170	J	UL
GEON WJJP623	75	1.68	-5	46	2000	170	D	53	170	J	
GEON WJJP626	75	1.61	0	50	2600	160	D	64	170	J / I	UL

1-800-GET-GEON  
SALES@GEON.COM



Copyright © 2021, GEON Performance Solutions. GEON Performance Solutions makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. GEON makes no warranties or guarantees respecting suitability of either GEON's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. GEON MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.